

**VICTORIA UNIVERSITY**  
MELBOURNE AUSTRALIA

*Performance improvement of PVDF hollow fiber-based membrane distillation process*

This is the Accepted version of the following publication

Yang, Xing, Wang, Rong, Shi, Lei, Fane, Anthony G and Debowski, Marcin (2011) Performance improvement of PVDF hollow fiber-based membrane distillation process. *Journal of Membrane Science*, 369 (1-2). pp. 437-447. ISSN 0376-7388

The publisher's official version can be found at  
<http://www.sciencedirect.com/science/article/pii/S0376738810009749>  
Note that access to this version may require subscription.

Downloaded from VU Research Repository <https://vuir.vu.edu.au/25290/>







Fig. 1. DCMD experimental set-up



Original PVDF




Plasma modified




Chemically modified


(a) Outer surface 1000x



Original PVDF




Plasma modified




Chemically modified


(b) Inner surface 1000x



Original PVDF




Plasma modified




Chemically modified

(c) Cross-section 350x


Fig. 2. SEM pictures of the original and modified PVDF membranes:  
(a) Outer surface; (b) Inner surface; (c) Cross-section



(a) Original PVDF



(b) Plasma modified



(c) Chemically modified

Fig. 3. Pore size/pore size distribution of the original and modified membranes:  
(a) Original PVDF membrane; (b) Plasma modified membrane;  
(c) Chemically modified membrane




Fig. 4. Permeation flux vs. feed temperature  
(3.5 % NaCl solution as feed,  $Q_f=2.5 \text{ L}\cdot\text{min}^{-1}$ ,  $Q_p=0.4 \text{ L}\cdot\text{min}^{-1}$ ,  $T_p=298\text{K}$ .  $T_f=313\text{--}343\text{K}$ )




Fig. 5. Long-term performance of the original and two modified PVDF membranes (3.5 % NaCl solution as feed,  $Q_f=2.5 \text{ L}\cdot\text{min}^{-1}$ ,  $Q_p=0.4 \text{ L}\cdot\text{min}^{-1}$ ,  $T_p=298\text{K}$ .  $T_f=323\text{K}$ )




Fig. 6. Effect of feed circulating velocity on permeation flux (3.5 % NaCl solution as feed,  $v_f=0.82\text{--}3.06\text{ m}\cdot\text{s}^{-1}$  (module #1) and  $0.17\text{--}1.05\text{ m}\cdot\text{s}^{-1}$  (module #2),  $v_p=0.17\text{ m}\cdot\text{s}^{-1}$ ,  $T_p=298\text{K}$ ,  $T_f=323\text{K}$ )




Fig. 7. Effect of permeate circulating velocity on permeation flux  
(3.5% NaCl solution as feed  $v_f=0.2 \text{ m}\cdot\text{s}^{-1}$   $v_p=0.04\sim 0.61 \text{ m}\cdot\text{s}^{-1}$ ,  $T_p=298\text{K}$ ,  $T_f=323\text{K}$ )







Fig. 8. Fluxes of small and big modules at different Re (3.5% NaCl solution as feed,  $Q_f=3 \text{ L}\cdot\text{min}^{-1}$ ,  $Q_p=0.4 \text{ L}\cdot\text{min}^{-1}$ ,  $T_p=298\text{K}$ )



(a)  $C$  and  $R_i$  vs. fiber length  $L$



(b) The bulk and membrane wall temperature distributions along fiber length



(c) Thermal boundary layer build-ups along the fiber length

Fig. 9. Effect of fiber length: (3.5 % NaCl solution as feed,  $Q_f=0.25 \text{ L} \cdot \text{min}^{-1}$  ( $Re_f=992$ ),  $Q_p=0.017 \text{ L} \cdot \text{min}^{-1}$  ( $Re_p=387$ ),  $T_p=298\text{K}$ ,  $T_f=323\text{K}$ ):

- (a)  $C$  and  $R_i$  vs. fiber length  $L$ ; (b) The bulk and membrane wall temperature distributions along fiber length; (c) Thermal boundary layer build-ups along the fiber length




Fig. 10. Relationship between the MD coefficient and module packing density  $\Phi$  (3.5 % NaCl solution as feed  $Q_f=2.5 \text{ L}\cdot\text{min}^{-1}$ ,  $Q_p=0.4 \text{ L}\cdot\text{min}^{-1}$ ,  $T_p=298\text{K}$ ,  $T_f=323\text{K}$ )

Table 1 Module specifications for all performance tests

Module No	Housing diameter, $d_s$	Membrane type	No of fibers, $n$	Effective fiber length L, mm	Packing density $\Phi$ , %	Membrane area $A$ , m <sup>2</sup>	Remark
#1	9.5 mm	Original /modified	20	225	50	0.022	Flux tests, circulating velocity and module size comparison
#2	19 mm	Original	80	360	50	0.135	Module size comparison
#3	9.5 mm	Original	1	150-1020	--	--	Single fiber tests
#4	19 mm	Original	--	450/650	3.5-71	--	Packing density tests

Table 2 Comparison of three types of hollow fiber membranes

Membrane type	Dimension	Contact angle (°)	Porosity $\epsilon$ (%)	LEP <sub>w</sub> (Bar)	Tensile modulus $E_t$ , MPa	Strain at break $\delta_b$ , %
Original PVDF	OD:1.47mm $\delta$ :275 $\mu$ m	88	85	1.38	44.60	98.60
Plasma Modified	OD:1.47mm $\delta$ :275 $\mu$ m	105	83	3.86	41.05	102.08
Chemically modified	OD:1.47mm $\delta$ :275 $\mu$ m	115	80	3.64	45.06	121.94